

Grade	8 X 16	6 X 12	6 X 16
Size (ASTM 2862)	Over Size = 4% max	Over Size = 4% max	Over Size = 4% max
	Under Size = 1% max	Under Size = 1% max	Under Size = 1% max
Moisture (ASTM 2867)	5% max	5% max	5% max
Apparent Density (ASTM 2854)	450 to 550 g/l	450 to 550 g/l	450 to 550 g/l
CTC (ASTM 3467)	50/55 % min	50/55 % min	50/55 % min
Iodine Number (ASTM 4607)	1000/1100 mg/g min	1000/1100 mg/g min	1000/1100 mg/g min
Ash (ASTM 2866)	3% max	3% max	3% max
pH (ASTM 3838)	9 to 11	9 to 11	9 to 11
Hardness (ASTM 3802)	99/98 % min	99/98 % min	99/98 % min
Abrasion Resistance (Anglo gold)	2% max	2% max	2% max
Platelet Content (Anglo gold)	7% max	7% max	7% max
D50	1.6 mm to 1.8 mm	2.2 mm to 2.6 mm	-

- 금회수